

Listing of Claims:

Claims 1 to 10 (canceled).

New Claims 11 to 28:

11. (new): A poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block comprising in combination:
- i) a polystyrene content from 15% to 20% by weight;
  - ii) a coupling efficiency from 50 to 80%;
  - iii) a step I molecular weight from 9,000 to 10,000 kg/mol;
  - iv) a vinyl content from 20 to 45%; and
  - v) a melt flow rate of equal to or greater than 10.
12. (new): The polymer of claim 11 wherein the polystyrene content is from 16 to 19% by weight.
13. (new): The polymer of claim 11 wherein the polystyrene content is from 16 to 18% by weight.
14. (new): The polymer of claim 11 wherein the coupling efficiency is from 60 to 75%.
15. (new): The polymer of claim 11 wherein the coupling efficiency is from 65 to 70%.
16. (new): The polymer of claim 11 wherein the vinyl content is from 25 to 40%.
17. (new): The polymer of claim 11 wherein the vinyl content is from 30 to 35%.
18. (new): The polymer of claim 12 wherein the vinyl content is from 25% to 40%.

19. (new): The polymer of claim 18 wherein the coupling efficiency is from 60% to 75%.

20. (new): The polymer of claim 17 wherein the polystyrene content is from 16% to 18% by weight.

21. (new): A hot melt adhesive composition comprising:

a) a poly(styrene-butadiene-styrene) polymer having a high vinyl content in the butadiene block, said polymer having:

- i) a polystyrene content from 15% to 20% by weight;
- ii) a coupling efficiency from 50 to 80%;
- iii) a step I molecular weight from 9,000 to 10,000 kg/mol;
- iv) a vinyl content from 20 to 45%; and
- v) a melt flow rate of equal to or greater than 10.

b) a tackifying resin;

c) an optional plasticizer; and

d) an anti-oxidant.

22. (new): The hot melt adhesive composition of claim 21 wherein the polymer has the following characteristics:

- i) a polystyrene content from 16% to 19%;
- ii) a coupling efficiency from 60% to 75%;
- iii) a step I MW from 9,400 to 9,600 kg/mol; and
- iv) a vinyl content from 25% to 40%.

23. (new): The hot melt adhesive composition of claim 21 wherein the polymer has the following characteristics:

- i) a polystyrene content of about 19%;
- ii) a coupling efficiency of about 70%;
- iii) a step I MW of about 9,500 kg/mol; and

iv) a vinyl content of about 30%.

24. (new): The hot melt adhesive composition of claim 21 having

a) a hot melt viscosity at 170°C during 24 hours lower than 100 Pa.S (ASTM D3236-78);

b) a rolling back tack of 1 cm to 5 cm (ASTM D3121-73);

c) a flap test, 500 g weight, higher than 120 minutes (method described herein);

and

d) a HP 40°C, 1 kg weight, higher than 50 minutes (ASTM D3654-82).

25. (new): The hot melt adhesive composition of claim 21 wherein the tackifier is present in an amount from 50 to 200 parts by weight.

26. (new): The hot melt adhesive composition of claim 21 wherein the plasticizer is present in an amount is up to 100 parts by weight.

27. (new): The hot melt adhesive composition of claim 22 wherein the tackifier is present in an amount from 100 to 150 parts by weight.

28. (new): The hot melt adhesive composition of claim 22 wherein the plasticizer is present in an amount is up to 5 to 75 parts by weight.

Applicants respectfully request consideration of newly added claims 11 to 28.

Respectfully submitted,

Date: September 23, 2004

A handwritten signature in black ink, appearing to read 'Donna Blalock Holguin', is written over a horizontal line.

Donna Blalock Holguin  
Registration No. 38,082  
KRATON Polymers U.S. LLC  
3333 Highway 6 South  
Rm. CA-108  
Houston, Texas 77082  
(281) 668-3224 (phone)  
(281) 668-3155 (fax)